



EURASIA PETROL  
Trading of Petroleum Products

## PRODUCT DATA SHEET

Product Category	Product Name	Grade
Polymers	POLYETHYLENE – LDPE	2420 H

Property	Value	Unit	Test Method
Mass Density (23 °C)	0.924	g/cm <sup>3</sup>	ISO1183
Melt Flow Rate (190°C /2.16kg)	2.0	g/10min	ISO1133
Melting point	112	°C	ISO11357
Vicat softening temperature, A/50	95	°C	ISO306
Tensile Modulus of Elasticity	270	MPa	ISO527
Stress at Yield	11	MPa	ISO527
Shore D hardness	48	–	ISO868
Max. tensile strength MD	23	MPa	ISO527
Max. tensile strength TD	21	MPa	ISO527
Maximum elongation MD	580	%	ISO527
Maximum elongation TD	700	%	ISO527
Dart Drop Impact	110	g	ASTM D1709
Gloss ( 60°)	120	–	ASTM D2457
Haze (40µm film)	6.5	%	ASTM D1003

<b>Application</b>	Blown film - Fine shrink film - Food packaging FFS film and bags - Packaging film for sanitary articles - Freezer film - Lamination film - Surface protection film - Sealing layer-Injection Molding •Foamed Products •Blow molding
<b>Packaging</b>	25 Kg plastic bag



+90 24 22 44 55 85



www.Eurasiapetrol.com  
Info@Eurasiapetrol.com



Adnan menderes blv, Tahilpazarı neighborhood,  
Emka building, no:22, Muratpaşa, Antalya, Turkey.